



Technical Data Sheet

3M™ Aluminum Foil Label Material 7940

Product Description

3M™ Aluminum Foil Label Materials are durable, thin gauge aluminum designed to meet a wide range of difficult nameplate application requirements. 3M™ Aluminum Foil Label Materials 7940 utilizes 3M™ Adhesive 320 which offers excellent adhesion to a variety of surfaces including high surface energy (HSE) and low surface energy (LSE) plastics.

Product Features

- The liner for 3M label material 7940 provides easy sheet processing and is designed for layflat. The backside of the liner is not printable.
- UL Recognized file MH11410

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.




Typical Physical Properties

Property	Values	Additional Information
Adhesive Type	320 High Tenacity Acrylic	
Liner	90# Polycyd. bleached kraft sheet polyethylene coated on two sides	
Liner Thickness	0.17 mm	
Facestock	Matte Silver Aluminum Foil Vinyl TC	
Facestock Thickness	0.051 mm	
Adhesive Thickness	1.7 mil	
Adhesive Thickness	0.043 mm	
Facestock Thickness	2 mil	

Liner Thickness 6.7 mil

Convertability 3M™ High Tenacity Acrylic Adhesive 320 is specifically designed to be compatible with flexographic and thermal transfer technologies. Its aggressive tack properties, while desirable for the end use application, may require extra care during processing. Please refer to the die cutting/converting section of this data page or the “Guide to Converting and Handling Label Products” technical bulletin for additional information.

Typical Performance Characteristics

Property	Values	Additional Information
90° Peel Adhesion Aluminum	6.8 N/cm	View 
<p>Test Method: ASTM D3330</p> <p>Test Name: 90° Peel Adhesion Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Aluminum Backing: 2 mil PET</p> <p>Notes: 12 in/min (300 mm/min)</p>		
90° Peel Adhesion Aluminum	62 oz/in	View 
<p>Test Method: ASTM D3330</p> <p>Test Name: 90° Peel Adhesion Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Aluminum Backing: 2 mil PET</p> <p>Notes: 12 in/min (300 mm/min)</p>		
90° Peel Adhesion Polypropylene (PP)	5.8 N/cm	View 
<p>Test Method: ASTM D3330</p> <p>Test Name: 90° Peel Adhesion Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Polypropylene (PP) Backing: 2 mil PET</p> <p>Notes: 12 in/min (300 mm/min)</p>		
Long Term Temperature Resistance	121 °C	

Minimum Long Term Temperature Resistance -40 °C

Long Term Temperature Resistance 250 °F

Minimum Long Term Temperature Resistance -40 °F

Minimum Application Temperature 10 °C

Minimum Application Temperature 50 °F


Note Calipers are nominal values

90° Peel Adhesion 7.8 N/cm View 

Test Method: ASTM D3330

Dwell/Cure Time: 10.0
Dwell Time Units: min
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: ABS

Notes: 12 in/min (300 mm/min)

90° Peel Adhesion 71 oz/in View 

Test Method: ASTM D3330

Dwell/Cure Time: 10.0
Dwell Time Units: min
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: ABS

Notes: 12 in/min (300 mm/min)

90° Peel Adhesion 5.6 N/cm View 

Test Method: ASTM D3330

Dwell/Cure Time: 10.0
Dwell Time Units: min
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Aluminum

Notes: 12 in/min (300 mm/min)







90° Peel Adhesion 51 oz/in View 

Test Method: ASTM D3330

Dwell/Cure Time: 10.0
Dwell Time Units: min

Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Aluminum

Notes: 12 in/min (300 mm/min)

90° Peel Adhesion Stainless Steel	69 oz/in	View 
<p>Test Method: ASTM D3330</p> <p>Test Name: 90° Peel Adhesion Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Stainless Steel Backing: 2 mil PET</p> <p>Notes: 12 in/min (300 mm/min)</p>		
90° Peel Adhesion ABS	8 N/cm	View 
<p>Test Method: ASTM D3330</p> <p>Test Name: 90° Peel Adhesion Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: ABS Backing: 2 mil PET</p> <p>Notes: 12 in/min (300 mm/min)</p>		
90° Peel Adhesion Stainless Steel	7.5 N/cm	View 
<p>Notes: 12 in/min (300 mm/min) ASTM D3330 72 hour dwell on Stainless Steel at 23°C (72°F) and 50% RH Backing: 2 mil Polyester</p>		
90° Peel Adhesion Glass	8 N/cm	View 
<p>Test Method: ASTM D3330</p> <p>Test Name: 90° Peel Adhesion Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Glass Backing: 2 mil PET</p> <p>Notes: 12 in/min (300 mm/min)</p>		
90° Peel Adhesion Glass	73 oz/in	View 
<p>Test Method: ASTM D3330</p> <p>Test Name: 90° Peel Adhesion Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Glass Backing: 2 mil PET</p> <p>Notes: 12 in/min (300 mm/min)</p>		
90° Peel Adhesion Polypropylene (PP)	53 oz/in	View 


Test Method: ASTM D3330

Test Name: 90° Peel Adhesion
Dwell/Cure Time: 72.0
Dwell Time Units: hr
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Polypropylene (PP)
Backing: 2 mil PET

Notes: 12 in/min (300 mm/min)

90° Peel Adhesion ABS

73 oz/in

View 

Test Method: ASTM D3330

Test Name: 90° Peel Adhesion
Dwell/Cure Time: 72.0
Dwell Time Units: hr
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: ABS
Backing: 2 mil PET

Notes: 12 in/min (300 mm/min)

90° Peel Adhesion

6.3 N/cm

View 


Test Method: ASTM D3330

Dwell/Cure Time: 10.0
Dwell Time Units: min
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Stainless Steel

Notes: 12 in/min (300 mm/min)

90° Peel Adhesion

58 oz/in

View 

Test Method: ASTM D3330

Dwell/Cure Time: 10.0
Dwell Time Units: min
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Stainless Steel

Notes: 12 in/min (300 mm/min)

90° Peel Adhesion

4.3 N/cm

View 

Test Method: ASTM D3330

Dwell/Cure Time: 10.0
Dwell Time Units: min
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Polypropylene (PP)

Notes: 12 in/min (300 mm/min)

90° Peel Adhesion

39 oz/in

View 


Test Method: ASTM D3330

Dwell/Cure Time: 10.0
Dwell Time Units: min
Temp C: 23C
Temp F: 72F

Environmental Condition: 50%RH
Substrate: Polypropylene (PP)

Notes: 12 in/min (300 mm/min)

90° Peel Adhesion	6.9 oz/in	View 
<p>Test Method: ASTM D3330</p> <p>Dwell/Cure Time: 10.0 Dwell Time Units: min Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Glass</p> <p>Notes: 12 in/min (300 mm/min)</p>		

90° Peel Adhesion	63 oz/in	View 
<p>Test Method: ASTM D3330</p> <p>Dwell/Cure Time: 10.0 Dwell Time Units: min Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Glass</p> <p>Notes: 12 in/min (300 mm/min)</p>		

Typical Environmental Performance

Property	Values	Additional Information
Chemical and Environmental Exposure	<p>Liquid Dwell Time/Exposure Condition Results</p> <p>Isopropyl Alcohol @ Room Temperature 4 hours No change</p> <p>Long term (days) Not recommended</p> <p>Isopropyl Alcohol @ Room Temperature 3 days 4 mm edge penetration</p> <p>Engine Oil @ Room Temperature 3 days No change</p> <p>Weak Acid (pH4) @ Room Temperature 3 days No change</p> <p>Weak Base (pH10) @ Room Temperature 3 days No change</p> <p>Water @ Room Temperature 3 days No change</p> <p>Acetone, gasoline and mineral spirits 4 hours 1-3 mm edge penetration</p> <p>Long term (days) Not recommended</p>	
Humidity Resistance	<p>3 days at 90°F (32°C) and 90% relative humidity: No change</p>	
Temperature Resistance	<p>100°F (38°C) for 1 day: No change</p> <p>300°F (149°C) for 1 day: Some yellowing of top-coat</p> <p>-40°F (-40°C) for 1 day: No change</p>	

Printing

All versions of 3M™ Aluminum Foil Label Materials are equipped, print-ready, with a vinyl topcoating. This topcoating is printable with conventional or UV inks using flexographic, letterpress, or screen printing processes. It is also capable of embossing with dot matrix impact printers. Whenever printing for the first time, with a different ink system or on a new machine, we strongly recommend carrying out proofing trials to validate ink adhesion and durability prior to a full production run.

Converting

Die Cutting:

3M™ Aluminum Foil Label Materials 7940 : Flatbed, matched metal dies, steel rule

Dispensing:

The liners for 3M™ Aluminum Foil Label Materials are designed for manual or semi-automatic. Be sure to properly test the materials in the particular process to determine suitability. Note that when manually dispensing, pull the liner away from the face to avoid bending the foil face into a permanent shape.

Storage and Shelf Life

Store at room temperature conditions of 72°F (22°C) and 50% relative humidity.

If stored under proper conditions, product retains its performance and properties for 24 months from date of manufacture.

Industry Specifications

UL Recognized, File PGGU2.MH11410, Marking & Labeling System Materials - Component, ANSI/UL 969

Bottom Matter

3M

Industrial Adhesives and Tapes Division

3M Center, Building 225-3S-06

St. Paul, MN 55144-1000

800-362-3550

Trademarks

3M is a trademark of 3M Company.

Handling/Application Information

Application Examples

- Inexpensive metal nameplate alternative for appliance, electronics, automotive and aircraft industries.
- Durable OEM decals.
- Serialized rating plates where extremely high bond and long term stability are needed.
- Embossed seals.

Application Techniques

- While the aluminum foil has excellent abrasion resistance, the use of overlaminating films can enhance performance.
- Foil nameplates should be as flat as possible before application. Any curl in the plate prior to application will remain in the metal memory and could lead to lifting at the edges. It is desirable to remove the liner from the nameplate by peeling it back at 180° and allowing the nameplate to project in a flat plane.
- For maximum bond strength, surface should be thoroughly clean and dry. A typical cleaning solvent is heptane or isopropyl alcohol. Note: Consult the manufacturer's MSDS for proper handling and storage of solvents. For best bonding conditions, application surface should be at room temperature or higher. Low temperature surfaces, (below 50°F [10°C]), can cause the adhesive to become so firm that it will not develop maximum contact with the substrate. Higher initial bonds are achieved through increased rubdown pressure.

References

Property	Values
3m.com Product Page	https://www.3m.com/3M/en_US/p/d/b5005329185/
Safety Data Sheet SDS	https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=7940

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.