

September, 2019

## 3M™ Computer-Imprintable Polyester Label Material 7883

### Product Features

- Topcoated polyester is compatible with dot matrix printing and is hand writeable. The matte coating resists degradation from scuffing, chemicals, moisture, and wide temperature fluctuations. The topcoat also provides improved ink anchorage for traditional forms of press printing.
- #300 adhesive bonds well to a wide variety of substrates including metals, high surface energy (HSE) plastics and low surface energy (LSE) plastics. It is ideal for applications requiring high initial adhesion especially to LSE plastic surfaces.
- 55# densified kraft liner assures consistent die cutting.
- 3M™ Label Material 7883 is UL recognized (Files MH11410 and MH16411) and CSA accepted (File 99316). See the UL and CSA listings for details.



## Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

## Typical Physical Properties

Property	Values	
Facestock	Matte silver polyester	
Facestock Thickness	0.084 mm	3.3 mil
Adhesive	#300 Acrylic	
Adhesive Thickness	0.02 mm	0.8 mil
Liner	55# Densified kraft	
Liner Thickness	0.081 mm	3.2 mil

## Note

Calipers are nominal values

## Special Considerations

For maximum bond strength, the surface should be clean and dry. Typical cleaning solvents are heptane and isopropyl alcohol.\*\*

\*\*NOTE: When using solvents, read and follow the manufacturer's precautions and directions for use.

For best bonding conditions, application surface should be at room temperature or higher. Low temperature surfaces, below 50°F (10°C), can cause the adhesive to become so firm that it will not develop maximum contact with the substrate. Higher initial bonds can be achieved through increased rubdown pressure.

## Typical Performance Characteristics

180° Peel Adhesion		Dwell/Cure Time	Substrate	Dwell Time Units	Temp C	Temp F	Environmental Condition	Notes
5.3 N/cm	48 oz/in	20 min @ Room Temperature	Stainless Steel					
4.6 N/cm	42 oz/in	20 min @ Room Temperature	ABS					
4.6 N/cm	42 oz/in	20 min @ Room Temperature	Polycarbonate (PC)					
4.2 N/cm	39 oz/in	20 min @ Room Temperature	Polypropylene (PP)					
4.1 N/cm	37 oz/in	72	Polycarbonate (PC)	hr	22C	72F	52%RH	12 in/min (300 mm/min)
4 N/cm	37 oz/in	72	ABS	hr	22C	72F	52%RH	12 in/min (300 mm/min)

Table continued on next page

## Typical Performance Characteristics (continued)

180° Peel Adhesion		Dwell/Cure Time	Substrate	Dwell Time Units	Temp C	Temp F	Environmental Condition	Notes
4.2 N/cm	38 oz/in	72	Polypropylene (PP)	hr	22C	72F	52%RH	12 in/min (300 mm/min)
3.7 N/cm	34 oz/in	72	Stainless Steel	hr	22C	72F	52%RH	12 in/min (300 mm/min)
3.2 N/cm	29 oz/in	72 hr @ 100°F(37°C) at 100% Relative Humidity	Stainless Steel					
3.3 N/cm	30 oz/in	72 hr @ 100°F(37°C) at 100% Relative Humidity	Polycarbonate (PC)					
5.4 N/cm	50 oz/in	72 hr @ 100°F(37°C) at 100% Relative Humidity	Polypropylene (PP)					
3.3 N/cm	31 oz/in	72 hr @ 100°F(37°C) at 100% Relative Humidity	ABS					

Property: 180° Peel Adhesion  
Method: ASTM D3330

180° Liner Release		Test Condition
0.054 N/cm width	14 g/in width	90 in/min
0.069 N/cm width	18 g/in width	300 in/min

Property: 180° Liner Release

## Typical Environmental Performance

## Chemical and Environmental Exposure

The properties defined are based on four hour immersions at room temperature (72°F/22° C) unless otherwise noted. Samples were applied to stainless steel panels 24 hours prior to immersion and were evaluated one hour after removal from the solution for peel adhesion. Adhesion measured at 180° peel angle (ASTM D 3330) at 12 inches/minute.

**Typical Environmental Performance (continued)**

Chemical	Adhesion to Stainless Steel		Appearance	Edge Penetration
	Oz./in.	N/100 mm	Visual	Millimeters
Isopropyl Alcohol	60	66	No change	0.8
Detergent 1% Alconox® Cleaner	64	70	No change	0
Engine Oil (10W30) @ 250°F (121°C)	64	70	No change	1
Water for 48 hours	66	72	No change	0
pH 4	65	71	No change	0
pH 10	64	70	No change	0
Formula 409® Cleaner	64	70	No change	0
Toluene	33	36	No change	6.5
Acetone	47	51	No change	4.3
Brake Fluid	74	81	No change	0
Gasoline	36	39	No change	5.8
Diesel Fuel	62	68	No change	1
Mineral Spirits	54	59	No change	2.4
Hydraulic Fluid	66	72	No change	0

**Humidity Resistance**

24 hours at 100°F (38°C) and 100% relative humidity: no significant changes in appearance or adhesion

**Temperature Resistance**

300°F (149°C) for 24 hours: no significant visual change

-40°F (-40°C) for 10 days: no significant visual change

Accelerated Aging		Notes
0.062 N/cm	16 g/in	180° Removal of Liner from Facestock at 90 in/min
5.9 N/cm	54 oz/in	180° Peel Adhesion from Stainless Steel at 12 in/min

Property: Accelerated Aging

Method: ASTM D3611

Test Condition : 96 hr @ 150°F (65°C) and 80% relative humidity

**Processing****Printing:**

Facestock is topcoated for improved ink receptivity and is designed for dot matrix printing. It is printable by all standard roll processing methods including flexography, hot stamp, letterpress, and screen printing. Refer to the Graphic Ink Selection Guide or call 3M Customer Service at 1-800-223-7427 for additional information.

**Die Cutting:**

Rotary die cutting is recommended. Fanfolding of labels is not recommended. Small labels should be evaluated carefully. Winding tensions should be kept at a minimum to help prevent the adhesive from oozing.

**Packaging:**

Finished labels should be stored in plastic bags.

**Agency Listing Information****Dot Matrix Printing:**

\*UL recognized and CSA accepted component for indoor and outdoor use. The following ribbons are UL recognized when used with this material.

● CGL-79™ from Mid-City Columbia, 800-462-2336 or 800-996-4656

● Ranger 288 from Herbert Dehinton & Co., 847-998-8150

3M does not recommend the Ranger 288 ribbon for bar code printing.

**Laser Toner Printing:**

UL recognized with the following printers and toners.

\*Toner and Printer/UL Recognized Components

Hitachi HMT 446 toner kit for producing finished printed labels with UL listed Synergystex CF-1000 laser printer

# 3M™ Computer-Imprintable Polyester Label Material 7883

## Handling/Application Information

### Application Ideas

- Barcode labels and rating plates.
- Property identification and asset labeling.
- Warning, instruction, and service labels for durable goods.
- Nameplates and durable goods.
- Substitutes for stamped metal, riveted plates.

### Storage and Shelf Life

24 months from date of manufacture of product when properly stored at 72°F (22°C) and 50% relative humidity.

### Industry Specifications

UL Recognized (Files MH11410 and MH16411)  
CSA Accepted (File 99316)

### References

#### Safety Data Sheet (SDS)

[https://www.3m.com/3M/en\\_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en\\_US&co=ptn&q=7883](https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=7883)

### ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

## Information

**Technical Information:** The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

**Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

**Warranty, Limited Remedy, and Disclaimer:** Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

